



Color Copy style with its natural shade provides an elegant impression to colour laser prints or copies as well as to superior monochrome prints. It is ideal for letterhead paper, business cards, invitations or compliment slips.




Technical Data: Color Copy style

Basis weight	g/m ²	ISO 536		160 ± 6.0
Caliper	µm	ISO 534		160 ± 6
Smoothness Bekk	sec	ISO 5627		105 ± 25
Opacity	%	ISO 2471	min	94.0
Brightness UV	%	ISO 2470		89.5 ± 2.0

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001, ISO 14001 and OHSAS 18001. Standard measurement uncertainty between laboratories is not incorporated.

SIGNIFICANCE OF VALUES: 2 SIGMA

*) .



Technical Data:		NEUTRAL WEISS		Grade: 754	
Basis weight	g/m ²	ISO 536		160	± 6.0
Caliper	µm	ISO 534		160	± 6
Smoothness Bekk	sec	ISO 5627		105	± 25
Opacity	%	ISO 2471	min	94.0	
Brightness UV	%	ISO 2470		89.5	± 2.0

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001, ISO 14001 and OHSAS 18001. Standard measurement uncertainty between laboratories is not incorporated.

SIGNIFICANCE OF VALUES: 2 SIGMA

*) .



Color Copy style with its natural shade provides an elegant impression to colour laser prints or copies as well as to superior monochrome prints. It is ideal for letterhead paper, business cards, invitations or compliment slips.




Technical Data: Color Copy style

Basis weight		g/m ²	ISO 536	100	± 4.0
Caliper		µm	ISO 534	106	± 4
Stiffness 15°/10mm	MD	mN	ISO 2493-1	160	± 30
Stiffness 15°/10mm	CD	mN	ISO 2493-1	85	± 25
Smoothness Bekk		sec	ISO 5627	105	± 25
Opacity		%	ISO 2471	min	86.0
Brightness UV		%	ISO 2470	89.5	± 2.0

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001, ISO 14001 and OHSAS 18001. Standard measurement uncertainty between laboratories is not incorporated.

SIGNIFICANCE OF VALUES: 2 SIGMA

*) .



Technical Data:		NEUTRAL WEISS			Grade: 754	
Basis weight		g/m ²	ISO 536		100	± 4.0
Caliper		µm	ISO 534		106	± 4
Stiffness 15°/10mm	MD	mN	ISO 2493-1		160	± 30
Stiffness 15°/10mm	CD	mN	ISO 2493-1		85	± 25
Smoothness Bekk		sec	ISO 5627		105	± 25
Opacity		%	ISO 2471	min	86.0	
Brightness UV		%	ISO 2470		89.5	± 2.0

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001, ISO 14001 and OHSAS 18001. Standard measurement uncertainty between laboratories is not incorporated.

SIGNIFICANCE OF VALUES: 2 SIGMA

*) .



Color Copy style with its natural shade provides an elegant impression to colour laser prints or copies as well as to superior monochrome prints. It is ideal for letterhead paper, business cards, invitations or compliment slips.



Technical Data: Color Copy style

Basis weight	g/m ²	ISO 536	200	± 6.0
Caliper	µm	ISO 534	200	± 7
Smoothness Bekk	sec	ISO 5627	130	± 40
Brightness UV	%	ISO 2470	89.0	± 2.0

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001, ISO 14001 and OHSAS 18001. Standard measurement uncertainty between laboratories is not incorporated.

SIGNIFICANCE OF VALUES: 2 SIGMA

*) .



Technical Data: NEUTRAL WEISS			Grade: 757	
Basis weight	g/m ²	ISO 536	200	± 6.0
Caliper	µm	ISO 534	200	± 7
Smoothness Bekk	sec	ISO 5627	130	± 40
Brightness UV	%	ISO 2470	89.0	± 2.0

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001, ISO 14001 and OHSAS 18001. Standard measurement uncertainty between laboratories is not incorporated.

SIGNIFICANCE OF VALUES: 2 SIGMA

*).